

COUPLER MATERIAL

FLUID	NY-GLASS	POLY-GLASS	PVC	PVDF
Plating Solutions, Chrome		S		
Potassium Acetate		S		
Potassium Chloride	S	S	S	S
Potassium Cyanide	S	S	S	
Potassium Dichromate	U	S	S	S
Potassium Fluoride	S	S	S	
Iodide, Peroxide		S		
Potassium Hydroxide, 30%	S	S	S	
Potassium Nitrate	S	S	S	S
Potassium Sulfate	S	S		S
Propane	S	S	S	
Propionic Acid	S	S		
Propylene Glycol	S	S		
Rosin	S	S		
Salt Water	S	S	S	S
Shellac	S	S		
Silicone Fluid	S			
Silicone Oil	S	S		
Silver Nitrate	S	S	S	S
Soap Solutions	S	S	S	
Soda Ash	S	S		
Sodium Bicarbonate	S	S	S	
Sodium Bisulfate		S	S	
Sodium Borate	S	S		
Perborate	S	S		
Sodium Carbonate	S	S	S	S
Sodium Chloride	S	S	S	S
Sodium Cyanide, 10%	S	S	S	S
Sodium Dichromate, 10%		S		
Sodium Hydroxide, 40%	S	S	S	
Sodium Hypochlorite, 20%	U	S	S	
Sodium Metaphosphate	S	S		
Sodium Nitrate	S	S	S	S
Sodium Peroxide		S	S	
Sodium Phosphate-				
Mono-Basic		S		
Di-Basic		S		
Tri-Basic		S		
Sodium Silicate		S		S
Sodium Sulfate	S	S	S	S
Sodium Sulfide		S	S	
Sodium Thiosulfate		S	S	S
Soybean Oil	S	S		
Stannic Chloride	U	S	S	
Stannous Chloride, 15%	U	S		
Steam				
Stearic Acid		S	S	
Stoddard Solvent			U	
Styrene				
Sugar Liquors-Cane	S	S		
Beet	S	S		
Sulfate Liquors		S		

COUPLER MATERIAL

FLUID	NY-GLASS	POLY-GLASS	PVC	PVDF
Sulphite Liquors		S	S	
Sulfuric Acid	U	S		S
Sulfurous Acid	U	S	S	
Superphosphate		S		
Tannic Acid, 10%		S	S	S
Tar-Wood		S		
Tartaric Acid	S	S	S	S
Titanium Tetrachloride-				
Dry		S	U	
Toluene/Toluol	S		S	
Tetrachlorethylene	S			
Trichloroethylene-Dry	S			
Triethanolamine		S	S	S
Trisodium Phosphate	S	S	S	
Urea		S	S	S
Urine	S	S	S	
Varnish	S			
Vinegar	S	S	S	
Water-Acid Mine	S	S	S	
Deionized	S	S		
Demineralized	S	S		
Distilled	S	S		
Fresh	S	S		
Salt	S	S		S
White Liquor (Paper Ind)		S	S	
Wine	S	S	S	
Xylene/Xylol	S		U	
Zinc Chloride		S	S	S
Zinc Nitrate, Sulphate	S	S	S	S

LEGEND:

S - Satisfactory
P - Poor
U - Unsatisfactory
Blank - Not tested

