

RMV[®] Compound, Multi-Plied Monofilament HPC[™]

Excellence in flexibility and precision

- Goodyear's RMV compound is FDA/USDA compliant and offers:
 - superior resistance to animal fats, vegetable and mineral oils
 - high resin content offers state-of-the-art Melt-Weld fabrications
- Multi-Plied Monofilament carcass with HPC[™] technology improves belt versatility:
 - excellent transverse rigidity
 - superior tracking in both directions
 - resistance to edge wicking and curling
 - flexibility over small pulleys
 - Thermo-Flo[™] splicing capabilities
- Ideal for meat, poultry, bakery and vegetable products

Description	Plies	Working Tension		Approx. OAG		Weight		COF (approx.)	Pulley Dia.		Temp.	
		PIW*	KN/m	in.	mm	Lbs./Sq.ft.	Kg/Sq.m		In.	mm	°F	°C
RMV 100RM CLW	2	100	18	0.090	2.3	0.53	2.6	0.18	2.0	51	20-180	-7-82

*Elongation less than 2% at specified PIW

Description	Splicing Methods	Recommended Fasteners**		
		Clipper	Alligator	Staple
RMV 100RM CLW	Finger-over-finger, Finger, Bias Stepped, Skived Bias, Mechanical Fasteners	36SP or UCM36SP	7	62

** Fastener manufacturer should be consulted to review specific belt and application information