

# COMPRESSED SHEET CHEMICAL RESISTANCE CHART

MEDIUM	STYLE					
	200	300	240	500	6234	6234C
Condensate	A	A	A	A	A	A
Copper Sulphate	A	A	A	A	A	A
Creosote	B	B	B	A	C	C
Cresol	B	B	B	A	B	B
Cyclohexanol	B	B	A	A	A	A
Decalin	C	C	B	A	A	A
Dibenzylether	C	C	C	A	C	C
Dibutylphalate	C	C	B	A	A	A
Diesel Oil	C	C	B	A	A	A
Dimethylformamide	C	C	C	A	C	C
Diphyl, Dowtherm A	C	C	B	A	A	A
Dye Liquors (alkaline, neutral, acid)	A	A	A	A	A	A
Ethane	A	A	A	A	A	A
Ethyl Acetate	B	B	B	A	B	B
Ethyl Alcohol, Ethanol	A	A	A	A	A	A
Ethyl Chloride	C	C	B	A	B	B
Ethylene	A	A	A	A	A	A
Ethylene Chloride	B	B	B	A	C	C
Ethylene Glycol	A	A	A	A	A	A
Ethyl Ether	B	B	A	A	A	A
Freon 12	C	C	A	A	A	A
Freon 22	C	C	A	A	A	A
Formaldehyde	A	A	A	A	A	A
Formic Acid 10%	A	A	A	A	A	A
Formic Acid 85%	B	B	B	A	B	B
Glycerine	A	A	A	A	A	A
Heating Oil	C	C	B	A	A	A
Heptane	C	C	A	A	A	A
Hydraulic Oil (glycol based)	A	A	A	A	A	A
Hydraulic Oil (mineral)	C	C	A	A	A	A
Hydraulic Oil (phosphate ester based)	B	B	B	A	B	B
Hydrochloric Acid 20%	C	C	B	A	B	B
Hydrochloric Acid 37%	C	C	C	A	C	C
Hydrofluoric Acid 10%	C	C	B	A	C	C
Hydrofluoric Acid 40%	C	C	C	A	C	C
Hydrogen	A	A	A	A	A	A
Hydrogen Peroxide (up to 6% w/w)	A	A	A	A	A	A
Hydrogen Chloride (Dry)	A	A	A	A	A	A
Iso-octane	B	B	A	A	A	A
Iso-propyl Alcohol	A	A	A	A	A	A
Kerosene	C	C	A	A	A	A
Lactic Acid 50%	A	A	A	A	A	A
Linseed Oil	B	B	A	A	A	A
Magnesium Sulphate	A	A	A	A	A	A
Mallic Acid	A	A	A	A	A	A
Methane	A	A	A	A	A	A
Methyl Alcohol	A	A	A	A	A	A
Methyl Chloride	C	C	B	A	B	B
Methylene Chloride	B	B	C	A	C	C
Methyl Ethyl Ketone	C	C	B	A	B	B
Mineral Oil	C	C	A	A	A	A
Mineral Oil Type ASTM 1	B	B	A	A	A	A
Mineral Oil Type ASTM III	B	B	A	A	A	A
Monochlor Methane	C	C	B	A	B	B
Nitrogen	A	A	A	A	A	A
Naphtha	C	C	B	A	A	A
Nitric Acid 20%	C	C	C	A	C	C

MEDIUM	STYLE					
	200	300	240	500	6234	6234C
Nitric Acid 40%	C	C	C	B	C	C
Nitric Acid 96%	C	C	C	C	C	C
Octane	C	C	B	A	A	A
Oleic Acid	A	A	A	A	A	A
Oxalic Acid	C	C	B	A	B	B
Palmitic Acid	A	A	A	A	A	A
Pentane	C	C	A	A	A	A
Perchlorethylene	C	C	B	A	B	B
Petroleum	B	B	A	A	A	A
Petroleum Ether	B	B	A	A	A	A
Phenol	B	B	B	A	C	C
Phosphoric Acid	A	A	A	A	A	A
Phthalic Acid	A	A	A	A	A	A
Potassium Acetate	A	A	A	A	A	A
Potassium Carbonate	A	A	A	A	A	A
Potassium Chlorate	A	A	A	C	A	A
Potassium Chloride	A	A	A	B	A	A
Potassium Cyanide	A	A	A	C	A	A
Potassium Dichromate	A	A	A	B	A	A
Potassium Hydroxide	B	B	B	A	B	A
Potassium Hypochlorite	A	A	A	B	A	A
Potassium Nitrate	A	A	A	C	A	A
Potassium Permanganate	A	A	A	A	A	A
Producer Gas	B	B	A	A	A	A
Propane	B	B	A	A	A	A
Pydrol	C	C	A	A	A	A
Pyridine	B	B	C	A	C	C
Rape Seed Oil	B	B	A	A	A	A
Silicone Oil	A	A	A	A	A	A
Sea Water	A	A	A	A	A	A
Sodium Aluminate	A	A	A	A	A	A
Sodium Bicarbonate	A	A	A	A	A	A
Sodium Bisulphite	A	A	A	A	A	A
Sodium Chloride	A	A	A	A	A	A
Sodium Hydroxide	B	B	B	A	B	A
Sodium Silicate	A	A	A	A	A	A
Sodium Sulphate	A	A	A	A	A	A
Sodium Sulphide	A	A	A	A	A	A
Steam	B	B	B	B	B	A
Steric Acid	A	A	A	A	A	A
Sulphur Dioxide	B	B	B	A	C	B
Sulphuric Acid 20%	C	C	B	A	C	C
Sulphuric Acid 50%	C	C	C	A	C	C
Sulphuric Acid 96%	C	C	C	C	C	C
Sulputous Acid	B	B	B	A	B	B
Tanic Acid	A	A	A	A	A	A
Tartaric Acid	A	A	A	A	A	A
Tetrachlorethane	C	C	B	A	B	B
Tetralin	C	C	B	A	A	A
Toluene	C	C	B	A	A	A
Town Gas	B	B	A	A	A	A
Transformer Oil	B	B	A	A	A	A
Trichlor Ethylene	C	C	B	A	B	B
Turpentine	C	C	B	A	A	A
Vinyl Acetate	C	C	B	A	A	A
Water	A	A	A	A	A	A
Xylene	C	C	B	A	A	A

