

STYLE 1300 PURE NATURAL RUBBER SHEET

Color: Tan.

Features: A composition of specially blended compounds. Soft, pliable, capable of filling flange irregularities with the lightest bolt loads.

Surface: Smooth.

Equipment: All mating flanges.

Limitations: Temperatures to 200°F/93°C.

Remarks: Deforms easily and recovers readily.

STYLE 1405-50 DURO RED SILICONE RUBBER SHEET

Color: Red.

Features: This polysiloxane polymer contains no acid producing chemicals and is noncorrosive. Although silicone physical properties are modest at ambient temperatures, it does retain these properties at more severe conditions which would cause the failure of other elastomers.

Surface: Smooth.

Equipment: All mating surfaces.

Remarks: Excellent high and low temperature resistance.

1406-60 DURO RED SILICONE SHEET Same as 1405 except 60 Durometer.

STYLE 1607 VITON® RUBBER SHEET

Color: Black.

Features: This fluoro-elastomer sheet displays unusual resistance to oils and chemicals at elevated temperatures. **Surface:** Smooth.

Equipment: All mating surfaces.

Limitations: Temperatures from -40°F/-4°C to 500°F/260°C.

Remarks: A favorite for high temperature oils.

STYLE 3404-40 DURO NEOPRENE SHEET

Color: Black.

Features: This chloroprene composition has excellent weathering resistance, good oil resistance and good physical properties. 3404 is a 40 durometer sheet.

Surface: Smooth.

Equipment: All mating surfaces.

3405-50 DURO NEOPRENE SHEET Same as 3404 except 50 durometer hardness.

3406-60 DURO NEOPRENE SHEET Same as 3404 except 60 durometer hardness.

3407-70 DURO NEOPRENE SHEET Same as 3404 except 70 durometer hardness.

STYLE 3456 WHITE RUBBER SHEET

Color: White.

Features: A 60 durometer white rubber compound having the same qualities as 3406 except that it is white and may be used to prevent product discoloration.

Surface: Smooth.

Equipment: All mating surfaces.

Remarks: A popular rubber compound in food processing plants.