

TYPICAL SPECIFICATIONS

STYLE	20	900	1000N	1001N	1105	1205
Material	SBR	SBR Cloth Reinforced	Neoprene Cloth Reinforced	Neoprene Cloth Reinforced	EPDM	Nitrile
Durometer	80	80	70	60	60	50
Cloth Insert Plies	None	Cotton Duck 1 Ply per 1/16"	Polyester 1 Ply per 1/16"	Nylon 1 Ply per 1/16"	None	None
Approximate Weight per Sq. Yd. (1/16" Thick)	5.3 lbs	4.5 lbs	4.3 lbs	4.3 lbs	3.5 lbs	4.0 lbs
Available Widths	36" & 48"	48"	52"	56"	36"	48"
Available Thicknesses	1/16-1/4"	1/32-1/4"	1/16-1/4"	1/16-1/4"	1/32-1/4"	1/32-1/4"

STYLE	1300	1405	1607	3404	3456
Material	Natural	Silicone	Viton	Neoprene	Neoprene
Durometer	40	50	70	40	60
Cloth Insert Plies	None	None	None	None	None
Approximate Weight per Sq. Yd. (1/16" Thick)	3.6 lbs	3.5 lbs	5.5 lbs	4.3 lbs	4.8 lbs
Available Widths	36"	36" & 48"	36" & 48"	36" & 48"	36"
Available Thicknesses	1/16-1"	1/16-1/4"	1/16-1/4"	1/32-1"	1/16-1/4"

STYLE	440	445	STYLE	5000	5100	207
Typical Tensile ASTM 152 Across Grain	2000 psi	1000 psi	Material	Virgin PTFE	Mech. Grade PTFE	Wool Felt
Compressibility ASTM 36A	25% - 40%	40% - 50%	Approx. Wgt.	1/16" x Sq. Ft. .75 lbs	1/16" x Sq. Ft. .75 lbs	1/8 x Sq.Yd. 1.53 lbs.
Recovery ASTM 36A	Min. 40%	Min. 40%	Available Widths	48" x 48"	48" x 48"	72"
Oil Resistance (22 hrs. in ASTM No. 3 oil @ 70-85°F) Thickness Increase	5% Max.	5% Max.	Available Thickness	1/32"-1/4"	1/32"-1/8"	1/8"-1"
Fuel Resistance (22hrs. in ASTM Fuel B @ 70-85°F) Thickness Increase	5% Max.	5% Max.				

